

Inverse Method and Indentation to Measure Material Parameters

Yu Gu, Toshio Nakamura, Lubos Prchlik*, and Sanjay Sampath*

Department of Mechanical Engineering

*Department of Materials Science and Engineering

State University of New York at Stony Brook

supported by National Science Foundation, US Army Research Office, Caterpillar

SEM Graduate Student Symposium

Stony Brook, NY


May 6, 2002

Objective:

Establish a novel data-interpretation procedure based on an **inverse analysis** technique to determine material properties. Utilize experimental measurements of **instrumented micro-indentation**.

Highlights:

- ❑ **Kalman filter** for inverse analysis.
- ❑ Elastic-plastic **graded** material.
 - *Two phases: PSZ and NiCrAlY*
 - *Tested with FGM specimen*
- ❑ Elastic-plastic **anisotropic** material.
 - *Finite element verification*
 - *Proposed experimental procedure*




Previous Studies for Related Material Characterization

- ❑ Analytical and experimental tools to estimate the elastic properties of graded materials using instrumented micro-indentation. *Suresh et al. (1997); Giannakopoulos et al. (1997).*
- ❑ Rule-of-mixtures for ceramic/metal system. *Weissenbek et al. (1997).*
- ❑ Use elastic wave and progressive-learning neural network to determine material properties of FGM plates. *Liu et al. (2001).*
- ❑ Forward-reverse method and instrumented sharp indentation to characterize elastic-plastic properties for thin film and coating. *Dao et al. (2001).*
- ❑ Inverse analysis based on Kalman filter and instrumented micro-indentation for characterization of graded materials. *Nakamura et al. (2000).*


Measurement Process with Inverse Analysis

Post-process experimentally obtained records (indirect measurements) by an inverse analysis to extract unknown material parameters




Application to Graded Materials

- ❑ Specimen fabricated in Thermal Spray Center at Stony Brook.
- ❑ Measurements made at **MIT & NIST** using instrumented micro-indenters.
- ❑ **Different sizes** of indenters: $R_1=0.8$ mm, $R_2=2.4$ mm.
- ❑ Indented **load-displacement** relations are recorded.




Instrumented indentation at NIST




Cross section of FGM specimen
($t = 350\mu\text{m}$)

Instrumented-Indentation

Two Differently Sized Spherical Indenters




Measured load-displacement records from micro-indentations (averaged from 10 records)



Records of two indenters are required for accurate estimates (Nakamura et al, 2000)


Unknown Parameters of FGM

- Properties of PSZ and NiCrAlY are characterized separately using homogeneous specimens.



Compositional Variation

'n': defines volume fraction of PSZ via power-law




$n < 1 \Rightarrow$ greater amount PSZ

$n > 1 \Rightarrow$ greater amount NiCrAlY

S - e Relation Through-Thickness

'q': stress-strain transfer parameter




Reuss Model: $q = 0 \Rightarrow E = (V_1/E_1 + V_2/E_2)^{-1}$

Voigt Model: $q \rightarrow \infty \Rightarrow E = V_1E_1 + V_2E_2$

modified rule-of-mixtures: Suresh & Mortensen (1998)

Estimation Process



Use measured load-displacement records at 20 load increments



Data Interpretation

INVERSE ANALYSIS

*Kalman Filter
and FE Models*




Best Estimates

Identifies two unknown parameters

- ***Stress-strain relation (q)***
- ***Compositional variation (n)***

Kalman Filter Procedure

- Incremental process to obtain best estimates
- Straightforward implementation in Fortran code



Reference Data Set

⇒ to match the measured record with reference solutions


Measurement vector $D = (D_1, D_2)^T$ and its gradient d for a given set of m_1, m_2 at every time increment t

$$D_t = D_t(m_1, m_2) \quad \text{and} \quad d_t = \begin{pmatrix} \frac{\partial D_t(m_1, m_2)}{\partial m_1} \\ \frac{\partial D_t(m_1, m_2)}{\partial m_2} \end{pmatrix}$$

Choose suitable values for covariance matrix of observation R_t , (constant with t) and Initial covariance matrix P_o of estimated parameters.

Computational Analysis


- ❑ Generates reference data set since no closed-form solution available.
- ❑ 6,600 axisymmetric elements.
- ❑ Displacement controlled loading.
- ❑ Contact condition w/ no friction between indenter and FGM layer.
- ❑ Large deformation analysis.
- ❑ Carried out 16 separate calculations for different values of q & n .
- ❑ Bi-cubic Lagrangian interpolation functions to determine P - D relations for any values of q & n .



Estimated FGM Parameters


- **Kalman Filter** was carried out for 1,600 sets of initial estimates.
- In inverse analysis, 20 load increments are chosen as measurement data.

two load-displacement records




Kalman Filter

Intensity of converged initial estimates



Re-Verification with Estimated Parameters

Load-displacement from FE analysis and experimental record



Excellent match between experimental records and FE simulation using the parameters extracted from inverse analysis shows good accuracy.

Application to Anisotropic/Transversely Isotropic Materials

Many coating and thin films exhibits anisotropy due fabrication processes

Three Unknown Material Parameters


- ❑ **Ratio of Young's Moduli** in two directions
- ❑ **Yield Stress** in longitudinal direction
- ❑ **Yield Stress** in transverse direction

Non-Dimensionalized Parameters:

$$E_L^* = \frac{E_L}{E_T} - 0.5$$

$$s_{oT}^* = \frac{s_{oT}}{s_o} - 1$$

$$s_{oL}^* = \frac{s_{oL}}{s_o} - 1$$




L : longitudinal direction

T : transverse direction

Proposed Measurement Procedure

- Since there are more unknowns, P - D record is not sufficient to estimate the parameters, and **additional measurements** are required to make good estimates.
- Without making the experiments more complex, we choose to **add strain gages** to provide more information to Kalman Filter.




Required Measurements

- One **load-displacement** record
- Two **strain-displacement** records

Strain gages must be close enough to the indentation to detect changes due to anisotropic and elastic-plastic responses.


strain gage placements (unit in mm)





Planned Experiment Setup

- Thermally sprayed 1.6mm thick NiCrAlY on 2mm thick steel substrate
- Use 1/16 inch ($R = 0.8\text{mm}$) diameter indenter.
- Load up to $P = 600\text{N}$ at indentation depth of about $70\mu\text{m}$ (sufficient plasticity).

FE Simulation





FE Verification



Exact values:
 $(s_L^*, s_T^*, E_L^*) = (0.65, 0.45, 0.55)$

Kalman Filter




Summary

- ❑ A new procedure based on **inverse analysis** is introduced to measure **elastic-plastic** material properties of **graded** and **anisotropic** materials.
- ❑ The method uses **load-displacement** records of **instrumented indentation**.
- ❑ Parameters of graded material were determined using **experimentally measured** load-displacement records and **Kalman Filter**. Estimated properties **agrees** with the experimental records very well.
- ❑ Simulated study shows properties of elastic-plastic transversely isotropic materials can be estimated with **single indentation** when **strain measurements** near indentation were included.
- ❑ Kalman filter procedure can be **extended/modified** to determine other unknown parameters including geometrical dimensions (e.g., thickness).


Material Properties of PSZ and NiCrAlY

Linear Elastic PSZ



force-displacement results from both simulated analysis and experimental measurements


Elastic-Plastic NiCrAlY




two unknown parameters

Characterization of Elastic-Plastic NiCrAlY

- **Kalman Filter** was carried out for 1,600 sets of initial estimates.
- In inverse analysis, 20 load increments are chosen as measurement data.





intensity of converged initial estimates for NiCrAlY



force-displacement results from both simulated analysis and experimental measurements

Compare to the Estimation Using Single Indenter



Scattered regions of convergence → Inaccurate.


Measured Properties with Estimates

Estimated Parameters
 $q = 0.86, n = 0.98$




Material properties through thickness



Variation of V_{PSZ} through thickness



Stress-strain relation through thickness




FE Verification of Proposed Procedure



Kalman Filter




Final locations of all initial estimates: shown in 3 unknown parameter space



Actual values:
 $(S_L^*, S_T^*, E_L^*) = (0.65, 0.45, 0.55)$

Schematic of the Convergence during the Inverse Analysis

- Input of **three measurements** gives excellent rate of convergence.
- *Kalman Filter* performs well with **large measurement error/noise**.



Percentage of initial estimates which converged close to the actual values

Equivalent Plastic Strain

FE Simulation

indentation depth = 70µm

load ~ 600N

