Application)

FEATURES:

- · Alkyd-like hardness and durability
- · Excellent Semi-gloss and color retention
- · Low odor and water clean-up
- Excellent flow and leveling
- · High hiding
- · Non-yellowing
- · Washable and scrubbable with mild detergents
- · Rapid dry minimum downtime in plant operations
- · Good abrasion resistance
- · Bonds to glossy surfaces without sanding
- · Easy application brush, roll or spray
- All purpose finish for multiple surfaces
- Highly flexible resists peeling and chipping
- · Low VOC
- Dry fall properties (see Application for details)
- Performance alternate for Federal SpecificationTT-E-2784
- Good application over Inorganic Zinc

RECOMMENDED USES:

This all purpose, non-yellowing finish is ideal for use on walls, equipment, machinery, piping, structural steel, storage tanks, wood or metal trim, shutters, building exteriors, prefinished siding, furniture and metal fences. As a topcoat for ZinCoat (Inorganic Zinc Primers), when used over steel substrate. KoraTex-680 is ideal for protection of concrete or masonry in new or maintenance applications.

NOT RECOMMENDED FOR:

Immersion Service, Direct or indirect exposure to acids or alkalies without a suitable topcoat. Containment of aromatic solvents, strong mineral and organic acid or severely corrosive materials.

COMPATIBLE COATINGS

May be applied over most tightly adhering coatings. **ZinCoat** series Primers, **SanyMastics** and other as recommended. For specific topcoat recommendations, please consult your **SanyChem** Technical Service.

NOTE: A mist coat or tie is required to minimize topcoat bubbling.

ORDER INFORMATION: Prices may be obtained from **SanyChem Sales Representative** or main Office.

APPROXIMATE SHIPPING WEIGHT

Freight Classification: Paint

Packaging: 1 gallon 5 gallons KoraTex-680 12.0 lbs 55.0 lbs.

FLASH POINT (Pensky/Martiens Closed Cup)

Flash Point > 93 °C

SPECIFICATION DATA

• Solids Content By Volume : 36% ± 2%

• Theoretical Coverage Rate per Gallon: *

577 mil ft² (14.4 m² / I at 25 microns) 288 mil ft² (7.2 m² / I at 50 microns)

•Mixing and application losses will vary and must be taken into consideration when estimating job requirements.

· Volatile Organic Content (VOC) as supplied :

EPA METHOD 24

283 g/L.

These are nominal values.

• Temperature Resistance (Non-Immersion Service):

Continuous: 200°F (93 °C) Non-Continuous: 250°F (121 °C)

NOTE: At 250 °F and above, slight discoloration and loss of gloss is observed

• Recommended Dry Film Thickness Per Coat and system:

2 mils (50 microns).

NOTE: Additional thickness may be required over rough surfaces for appearance. Dry Film Thickness in excess of 3 mils/coat is not recommended.

• Color Standard in : Available in a variety of colors.

Some colors may require multiple

coats for adequate hiding.

• Gloss Semi-Gloss

• Substrates: Apply over properly primed steel,

concrete and masonry.

• Shelf Life: KoraTex-680 24 months when stored at 75

°F (25 °C)

KEEP FROM FREEZING

Storage Conditions: Store indoors.

Temp.: 40 - 110 °F (4 -43 °C)

Humidity: 0 - 100%

CHEMICAL RESISTANCE GUIDE KoraTex-680				
Exposure	Splash & Spillage	Fumes		
Acids	Fair	Good		
Alkalies	Good	Excellent		
Solvents	N/R	Very Good		
Water	Very Good	Excellent		
Salt	Very Good	Excellent		



January 2001 replaces April 1998

To the best of our knowledge the technical data contained herein is true and accurate on the date of publication and is subject to change without prior notice. User must contact **SanyChem** Company to verify correctness before specifying or ordering. No guarantee of accuracy is given or implied. We guarantee our products to conform to **SanyChem** quality control. We assume no responsibility for coverage, performance or injuries resulting from use. Liability, if any, is limited to replacement of products. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY SANYCHEM, EXPRESS OR IMPLIED, STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. **SanyChem** and **KoraTex** are registered trademarks of **SanyChem** Company.

APPLICATION INSTRUCTIONS

These instructions are not intended to show product recommendations for specific service. They are issued as an aid in determining correct surface preparation, mixing instructions, and application procedure. It is assumed that the proper product recommendations have been made. These instructions should be followed closely to obtain the maximum service from the materials.

Substrates & Surface Preparation

General: Remove any oil or grease from surface to be coated with clean rags soaked in SolvenSany # 252 Thinner or MetalCleaner # 100 in accordance with SSPC-SP-1.

Steel: Apply over clean, dry, recommended primers.

Concrete, Plaster and Masonry – Must cure at least 30 days before painting. pH must be 10.0 or lower. Roughen slick poured or precast concrete and remove sealers by chemical cleaning or abrasive method such as sandsweeping. Rinse thoroughly with water and allow to dry. Remove loose aggregate. Can be applied direct to concrete whre an uneven surface can be tolerated. Remove laitance by abrasive blasting or other means.

Previously Painted Surfaces: Wash to remove contaminants. Rinse thoroughly with water and allow to dry. Sanding is not required if the surface is properly and thoroughly cleaned (scuff sanding is required only on glossy, hard, slick or dense surfaces which are subject to high levels of moisture). Remove loose paint. Scrub heavy chalk exterior areas and overhead areas such as eaves with soap and water. All existing mildew must be removed by washing with a solution of 16 oz. (473 mL) liquid household bleach and two oz.(59 mL) non ammoniated liquid detergent per gallon (3.785 L) of water. Rinse surfaces clean with water and allow to dry for 24 hours. Prime bare areas with primer specified under New Surfaces. May be used self primed over previously painted interior surfaces.

Removal of old paint by sanding, scraping or other means may generate dust or fumes that contain lead. Exposure to lead dust or fumes may cause adverse health effects, especially in children or pregnant women. Controlling exposure to lead or other hazardous substances requires the use of proper protective equipment, such as properly fitted respirator (NIOSH approved) and proper containment and cleanup. For additional information, contact the USEPA/Lead Information Hotline at 1- 800-424-LEAD.

Mixing Power mix until uniform in consistency. Avoid

excessive air entrainment.

Designed to be used as supplied. If thinning is necessary, it may be thinned up to 12 oz/gal (10%) with potable water. Use of thinners other than those supplied or recommended by **SanyChem** may adversely affect product performance and void product warranty, whether

expressed or implied.

Application Equipment

Thinning:

Listed below are general equipment guidelines for the application of this product. Job site conditions may require modifications to these guidelines to achieve the desired results. The following equipment has been found suitable and is available from manufacturers such as Binks, DeVilbiss and Graco.

Application Equipment



Listed below are general equipment guidelines for the application of this product. Job site conditions may require modifications to these guidelines to achieve the desired results. General guidelines:

Spray Application (General)

The following spray equipment has been found suitable and is available from manufacturers such as Binks, DeVilbiss and Graco.

Conventional Spray

Use sufficient air volume for correct operation of equipment. Use 50% overlap with each pass of the gun. On irregular surfaces, coat the edges first, making an extra pass later. Pressure pot equipped with dual regulations, ½ I.D. minimum material hose, 0.086° I.D. fluid Tip and appropriate Air Cap.

Airless Spray

Graco Silver or Equivalent

 Pump Ratio:
 30:1 (min.)

 GPM Output:
 3.0 (min.)

 Material Hose:
 3/8" I.D. (min.)

 Tip Size:
 .017-.019"

 Output PSI:
 1800 -2200

 Filter Size:
 60 mesh

Teflon packings are recommended and available from the pump manufacturer.

Washing Instructions: Do not wash in less than seven days after application. Use a non-abrasive, mild detergent and water and a cellulose sponge. Do not attempt to clean the dried film with cleaners that contain ammonia and/or solvent such as window, tile or appliance cleaners.






For information and Prices, Please Call a SANYCHEM Local Sales Representative.



+58-212-6313092 | +58-414-3142752 | Fax: +58-212-6312441 | SanyChem, Inc

680 N Pine Island Road # 450 Plantation, FL 33324-1311 Phone +1- 954- 315- 0252 / +1 - 800-432-0607 / Fax: +1-954-315-0280



These times are based on recommended dry film thickness. High humidty, high film thickness or cooler temperatures will lengthen dry to handle/topcoat and final cure due to slower water evaporation rate.

APPLICATION TEMPERATURES						
Conditions	Material	Surfaces	Ambient	Humidity		
Normal	16-32 °C	18 -29 °C	18–32 °C	10-80%		
Minimum	10 °C	10 °C	10 °C	0 %		
Maximum	40 °C	54 °C	43 °C	85 %		

Do not apply when the surface temperature is less than 2 $^{\circ}\text{C}\,$ above the dew point



Brush: Use a synthetic bristle brush. Two coats will be required in order to achieve desired film thickness and acceptable hiding.



Roller: Use a short woven nap synthetic roller and apply over smooth wall surfaces and smooth concrete. For rough surfaces, cinder block or very porous surfaces, use a 3/8" woven nap synthetic roller. Multiple coats may be required for uniform hiding and film thickness over rough surfaces.

Cleanup & Safety

Cleanup

Use **Clean potable water**. In case of spillage, absorb and dispose of in accordance with local applicable regulations. Clean immediately with warm, soapy water.

WARNING! HARMFUL OR FATAL IF SWALLOWED. ASPIRATION HAZARD-CAN ENTER LUNGS AND CAUSE DAMAGE. HARMFUL IF INHALED. MAY CAUSE CENTRAL NERVOUS SYSTEM EFFECTS, INCLUDING DIZZINESS, HEADACHE OR NAUSEA. CAUSES EYE, SKIN AND RESPIRATORY TRACT IRRITATION. CAUSES EYE BURNS. CONTAINS CRYSTALLINE SILICA WHICH CAN CAUSE LUNG CANCER AND OTHER LUNG DAMAGE IF INHALED. OVEREXPOSURE MAY CAUSE BLOOD, LIVER, KIDNEY DAMAGE. USE ONLY WITH ADEQUATE VENTILATION. KEEP OUT OF THE REACH OF CHILDREN.

NOTICE: Products in this series contain solvents. Reports have associated repeated and prolonged occupational over exposure to solvents with permanent brain and nervous system damage. Intentional misuse by deliberately concentrating and inhaling the contents may be harmful or fatal. Products in this series may contain chemicals subject to California Proposition 65. If sanding is done, wear a dust mask to avoid breathing of sanding dust. Do not breathe vapors or spray mist. If you experience eye watering, headaches, or dizziness, leave the area. If properly used, a respirator may offer additional protection. Obtain professional advice before using. Close container after each use. FIRST AID: In case of skin contact, wash off quickly with plenty of soap and water, remove contaminated clothing. For eye contact flush immediately with large amounts of water, for at least 15 minutes. Obtain emergency medical treatment. If swallowed, obtain medical treatment immediately. If inhalation causes physical discomfort, remove to fresh air. If discomfort persists or any breathing difficulty occurs, get medical help. KEEP FROM FREEZING. Note: These warnings encompass the product series. Prior to use, read and follow product-specific MSDS and label information.

FOR INDUSTRIAL USE ONLY. KEEP AWAY FROM





Internet: www.sanychem.com sanychem@cantv.net sales@sanychem.com